

Parameter	Unit	Value		Test method
		min.	max.	
Penetration at 25 °C	0.1 mm	70	100	EN 1426
Softening point	°C	43	51	EN 1427
Fraass breaking point	°C	-	-10	EN 12593
Flash point	°C	230	-	EN 2592
Resistance to hardening at 163 °C: - retained penetration - increase in softening point - change of mass	% °C %	46 - -	- 9 0.8	EN 12607-1
Solubility	%	99.0	-	EN 12592
Dynamic viscosity at 60 °C	Pa*s	90	-	EN 12596
Kinematic viscosity at 135 °C	mm ² /s	230	-	EN 12595