

Parameter	Unit	Value		Test method
		min.	max.	
Cetane number	-	-	51.0	EN ISO 5165
Cetane index	-	-	46.0	EN ISO 4264
Density at 15 °C	kg/m ³	820.0	845.0	EN ISO 1285
Polycyclic aromatic hydrocarbons	%	-	8.0	EN 12916
Sulphur content	mg/kg	-	10.0	EN ISO 20846
Flash point	°C	55 >	-	EN ISO 2719
Carbon residue (on 10% distillation residue)	%	-	0.30	EN ISO 10370
Ash	%	-	0.01	EN ISO 6245
Water content	mg/kg	-	200	EN ISO 12937
Total contamination	mg/kg	-	24	EN 12662
Copper strip corrosion (3 h at 50 °C)	class	1		EN ISO 2160
Oxidation stability	g/m ³	-	25	EN ISO 12205
Lubricity, corrected wear scar diameter (wsd 1.4) at 60 °C	µm	-	460	EN ISO 12156-1
Viscosity at 40 °C	mm ² /s	2.00	4.50	EN ISO 3104
Fractional composition: - recovered at 250 °C - recovered at 350 °C - 95% (V/V) recovered at	% (V/V) % (V/V) °C	- 85 -	< 65 - 360	EN ISO 3405
CFPP: - Grade C - Grade F	°C	- -	-5 -20	EN 116